

Tabela1. Dozvoljeno strujno opterećenje užadi nadzemnih vodova na temperaturi +40 C

presjek (mm ²)	Bakar	Bronza	Aluminijum	Alučel	
	(A)	(A)	(A)	(mm ²)	(A)
6	60	40			
10	85	55			
16	115	80	90	16/2,5	90
25	150	105	120	25/4	125
35	175	125	150	35/6	145
50	230	165	185	50/8	170
70	280	200	225	70/12	235
95	360	255	285	95/15	290
120	410	290	330	120/21	345
150	480	340	380	150/25	400
185	545	385	435	185/32	455
240	640	455	515	240/40	530
300	750	530	600	300/50	615

Tabela 2. Korekциони faktor usled uticaja temperatura

Temperatura okoline	30	20	10	0
Korekциони faktor	1,12	1,22	1,30	1,41